



Guangdong Bolliya Metal Building Materials Co.,Ltd

No.9, Xingye Rd, Yanyuan Industry Zone, Xingtan Town, Shunde District, Foshan City, Guangdong, China
Tel: 0086 757 22890830 Fax: 0086 757 22890820

Technical Data Sheet

Aluminium Corrugated Core Panel

Basic information

Item	Value	Tolerance
Panel thickness	4mm	+/-0.2mm
Aluminum skin thickness	0.7mm + 0.5mm or 0.5mm + 0.5mm	+/-0.02mm
Aluminum alloy	3003 H16	
Core	Corrugated Aluminium Core	
Panel width	1250mm, 1500mm, 1575mm, 2000mm	+/-2mm
Panel length	1000mm to 5800mm	+/-3mm
Coating Types	PVDF	
Coating Thickness	25microns	+/-3microns
Panel weight	4.2 to 4.6 kgs/sq.m	+/-5%

Fire retardant Properties

Property	Test Method	Test result
External cladding	EN13501-1	class A2 s2 d0
External cladding	AS15301.1	Pass

Mechanical Properties (4MM with 0.7+0.5mm skin)

Suitable for Temperature		-50 to +80 °C
Tensile Strength of Aluminium Skin	ASTM E84	170Mpa
Elongation of Aluminium Skin	ASTM E84	8%
Tensile Strength of Panel	ASTM E84	0.8Mpa
Peel Torque	ASTM ED1781-98	265 mm N/mm ²
Acoustic Property	ISO 717-1	22 dB

Painting Dry Film Properties

Property	Test Method	Test result
60" gloss	ASTM D523-89	30-95
Formability(T-bend)	ASTM D1737-62	2
Hardness Pencil	ASTM D3363-92a	1-2H
Adhesion	ASTM D3359, Method 8	No change
Abrasion Resistance	ASTM D968-93(Falling Sand)	25 liter/mil
Chemical Resistance	ASTM D1308-79	No change
	ASTM D1308-79	No change
	AAMA 2605-05 Section 7.7.2	No change
	ASTM D2248-73	No change

Weatherability

Property	Test Method	Test result
Color Retention	ASTM D2244-93	Qualified
Gloss Retention	ASTM D523-89	Qualified
Chalking	ASTM D4214-89	Qualified
Salty Spray	ASTM D-B117-90&NCCA 11-2	Qualified
Humidity Thermal	ASTM D2246-65	Qualified
Humidity	ASTM D2247-94	Qualified
Condensing Humidity	ASTM D4585-87	Qualified